

## The Art of Expression since 1584

The Hahnemühle Digital FineArt Collection



### William Turner, 190 g/m<sup>2</sup>

Natural White, Genuine 'mould-made', 100% rag content

©2000 Jesús Vilallonga "Blue Malvi" – www.vilallonga.com

#### Product Description

Natural white mould-made watercolour paper with 100% rag content making it highly archival. A smooth surface that is perfectly suitable for detailed work and watercolours.

#### Applications and Characteristics

The printed side of this paper has been specially coated for excellent image sharpness and optimum colour graduation. The coating also offers a very high level of water resistance.

Common applications include:

Fine art reproduction, business cards, greetings cards, post cards, menu and Novelty applications, certificates and presentation prints for display purposes.

#### Physical Characteristics

	Unity	Valuation	Test Norm / Notes
Test Conditions		23°C / 50% R.H.	CSS14
Weight total	g/m <sup>2</sup>	190	ISO536
Thickness	mm	0,42	EN 20534
Whiteness	%	88,5	ISO 11475 (W <sub>cie</sub> / D65, 2°)
Opacity	%	96,5	DIN 53146
Media Colour		white	not bleached
pH-Value total		8,1	DIN 53124
Water resistance		very high	
Cobb		80,0	EN 20 535
Ink limit	%	245	
Special features		-	

All indicated data to be understood as typical average values.

#### Conditions of use and storage

Use and store at a relative humidity of 35 to 65% and a temperature of 10 to 30° C (50° – 86°F).

All recommendations and product indications are for your guidance, and are subject to our test criteria, these remain subject to change without prior notice. There is no guarantee that the same results can be consistent.

Use care in handling printed material, surface susceptible to abrasion.

Store papers in archive quality envelopes, folders, and boxes.

Use only archive grade tapes and glues for mounting & framing.